

TECHNICAL DATA SHEET

TOPECA, Lda Rua do Mosqueiro 2490-115 Cercal — Ourém PORTUGAL

Tel.: 00 351 - 249 580 070 Fax.: 00 351 - 249 580 079

geral@topeca.pt www.topeca.pt



bonding and grouting

colour joints for mosaic, tiles and bathroom fittings from 1 to 10mm





smooth texture

use

Damp proofing mortar for coloured joints in coverings, paving, swimming pools, bathroom fittings or any type of ceramic or natural stone.

Strong and smooth, crack-free joints (no sand).

surface

- Ceramics;
- · Natural Stone.



CE marking

CG2W European standards EN 13888



colour joints for mosaic, tiles and bathroom fittings from 1 to 10mm

bonding and grouting

recommendations

Do not apply Juntaemcor on tiles which have just been laid.

Do not apply when the weather is humid, during rain or in direct sunlight.

Different site conditions, surface humidity, absorption rates of tiles, drying times and different methods of application may give rise to differences in colour.

For joints which are submitted to heavy use, we recommend the use of Topcola Epoxy.

composition and characteristics

Composition:

Cement, synthetic resins, specific additives and pigments.

Characteristics:

Drying time: 3 hours.
Working time: 2-3 hours.

Waiting time necessary for use: 3 days. Time for general cleaning: 24 hours. Application temperature: +5 ° C to +30 ° C.

Bulk density: 1700 kg/m³

Compressive strength (28 days): >24.0

 N/mm^2 .

Flexural strength (28 days): >4.0

 N/mm^2 .

Water absorption after 30 minutes: < 2

g

Water absorption after 240 minutes: <5 g

Note: the results corresponding values obtained in the laboratory according to standard EN 13888, these conditions may vary with application.

colour

See table color grading.

consumption

See Table of consumption in this chapter.

available in

Box of 3 Kg – pallet with 120 boxes. Sacks of 10 Kg - pallet with 60 sacks.

storage

1 year from date of manufacture in a sealed packet stored in a damp free environment.



colour joints for mosaic, tiles and bathroom fittings from 1 to 10mm

bonding and grouting

preparation of surface

Surfaces must be clean, dry and free of mortar fixative so as to ensure even drying and uniformity of colour.

Respect dilation joints and separation systems on surfaces.

In the case of absorbent items, apply iTOP – surface protector.



application

Mechanically mix Juntaemcor with approximately 1L of water per 3 kg of Juntaemcor until an even and lump free paste is obtained. Adapt the consistency of the paste to the width of the joint. Wider joints require a thicker paste.



Apply within 3 hours after preparation, spreading the paste over the tiles diagonally using a rubber spatula. Continue until the joints are properly filled.



Wait for Juntaemcor to start to harden (approximately 20 minutes).

When the surface shine of the mortar disappears, smooth out the joints with a well-squeezed damp sponge. Do not use too much water when cleaning so as to avoid white streaking. After 15 minutes, clean the tiles with a dry cloth.

After 24 hours, general cleaning can be completed using a damp cloth.







colour joints for mosaic, tiles and bathroom fittings from 1 to 10mm


colours





colour joints for mosaic, tiles and bathroom fittings from 1 to 10mm


cores normais




3 kg - 104392 10 kg - 106592




3 kg - 108901 10 kg - 109101



3 kg - 109001 10 kg - 109201




3 kg - 101547 10 kg - 101548



3 kg - 105806 10 kg - 105808

prestige colours





107292



bonding and grouting

juntaemcor

colour joints for mosaic, tiles and bathroom fittings from 1 to 10mm

suggestion







Mix colored sands (see this catalog) to get together with a unique style.

The colors displayed are printing colors may be slightly different colors marketed. Special colors are dependent on quantity. The gradation may be found on shelves available from your dealer.

