# tuforte barramento

# sealing mortar



# tuforte .....

• reference thin

#### use

For sealing interior walls and ceilings which have fresh or dry cement finishes.

Tuforte Barramento is a product which improves the smooth finish of walls and ceilings with new cement coverings, in restoration work on new or old cement coverings as long as not already covered.

## surface

- Render;
- Concrete.







# tuforte barramento

## recommendations

Do not apply to frozen surfaces or when a risk of frost exists in next 24 hours. For plastic paint finishes on Tuforte Barramento, first apply:

- A suitable primer (e.g. Regulador de Fundo Topeca); or
- A coat of plastic paint (resin rich) diluted with 50% water.

Allow product to dry between application of successive layers (approximately 4 hours under normal conditions).

Do not apply Tuforte Barramento while drying process is underway.

# composition and characteristics

#### Composition:

Hydraulic binders, inert materials and specific fillers.

#### **Characteristics:**

Paste working time: 2 - 3 hours. Hardening time: 3 - 4 hours.

Application thickness: 0 - 2 mm.

Waiting time before coating: 2-3 days (when applied to dry cement)

Density of Powder: 0.95 g/cm<sup>3</sup>

Application temperature  $+5^{\circ}$ C a  $+30^{\circ}$ C.

NOTE: Results obtained in laboratory tests under normal conditions (T=20 $^{\circ}$ C). May vary depending on application conditions.

#### colour

White

#### consumption

1Kg/m<sup>2</sup> /mm of thickness.

## available in

Sacks de 20 Kg. Pallets with 48 sacks.

#### storage

1 year from date of manufacture in original sealed package.



#### Pág. 2

sealing mortar

application

# preparation of surface

Surfaces must be clean, solid and free of dust, paint, grease and efflorescence. Surfaces must be flat.

The sealing paste should be applied with a metal trowel.

water, until a mortar with good consistency is obtained.

Drying depends on atmospheric conditions (temperature and relative humidity) and absorption by surface.

Mix Tuforte Barramento using a mechanical mixer with approximately 13-14 litres of clean

The final layer may be sanded when dry.





